

A: Suitable for temperatures up to 60°C (= 140°F)
 B: Suitable for ambient temperatures (all over the world)
 C: Recommended for intermittent service only (Defined as ship to shore, ship to ship or road tanker transfer operations where the hose is not left full of product after use)
 D: Not suitable, or no sufficient data available

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
A													
ACETALDEHYDE		100	1089	75-07-0		D	C	C	A	C	D	A	A
ACETALDEHYDE		40	1089	75-07-0		D	A	A	A	A	D	A	A
ACETIC ACID		60	2790	64-19-7		D	A	A	A	A	D	A	A
ACETIC ACID		20									D	A	D
ACETIC ACID		GLACIAL	2790	64-19-7		D	B	B	A	B	D	A	A
ACETIC ANHYDRIDE		100	1715	108-24-7		D	B	B	A	B	D	A	A
ACETO ACETIC ESTER		100				D	B	B	A	B			
ACETONE		100	1090	67-64-1		A	A	A	A	A	A	A	A
ACETONE CYANOHYDRIN			1541	75-86-5		D	B	B	A	B	A	A	D
ACETONITRILE			1648	75-05-8		B	B	B	A	B	A	A	A
ACETOPHENONE		100	3265			B	B	B	A	B	A	A	A
ACETYLACETONE		100	2310	123-54-6		B	B	B	A	B	A	A	A
ACETYL CHLORIDE			1717	75-36-5		D	D	D	A	D			
ACETYLENE DICHLORIDE		100	1150	540-59-0		B	B	B	A	B	A	A	A
ACROLEIN		100	2607	107-02-8		B	B	B	A	B	A	A	A
ACRYLIC ACID			2218	79-10-7		D	B	B	B	B	D	A	A
ACRYLONITRILE		100	1093	107-13-1		A	A	A	A	A	D	A	A
ADIPIC ACID		SATURATED	FREE			A	A	A	A	A	D	A	A
ADIPONITRIL		100	2205	111-69-3		B	B	B	A	B	A	A	A
ALKYL BENZENE SULPHONIC ACID SOL.			2584			D	C	B	B	B			
ALLYL ALCOHOL		100	1098	107-18-6		A	A	A	A	A	A	A	A
ALLYL BROMIDE		100	1099	106-95-6		C	C	C	A	C	A	A	D
ALLYL CHLORIDE		100	1100	107-05-1		C	C	C	B	C	A	A	D
ALUMINIUM CHLORIDE SOL.		SATURATED	2581	7446-70-0		D	D	A	A	A	D	D	D
ALUMINIUM NITRATE		SATURATED				D	B	B	A	B	A	A	D
ALUMINIUM SALTS SOL.						D	A	B	A	B			
ALUMINIUM SULPHATE SOL			2796	10043-01-3		A	A	A	A	A			
ALUMS		SATURATED	3051			A	A	A	A	A	A	A	A
AMINOETHYL ETHANOLAMINE			2815	140-31-8		D	B	B	A	B	A	A	A
AMMONIA SOLUTION			1005	7664-41-7		D	A	A	A	A	A	A	D
AMMONIUM CHLORIDE		SATURATED	FREE			D	A	C	C	C	D	D	D
AMMONIUM HYDROXIDE			2506	35089-90-8		B	B	B	A	B			
AMMONIUM NITRATE SOL.			2426	6484-52-2		D	C	B	A	B			
AMMONIUM SALTS		SATURATED				D	A	B	B	B	A	A	D
AMMONIUM SULPHATE SOL.			FREE			A	A	A	A	A			
AMMONIUM SULPHIDE			2683	12124-99-1		A	A	A	A	A			
AMMONIUM THIOSULPHATE						A	A	A	A	A			
AMS		70				D	A	D	D	D			
AMYL ACETATE		100	1104	628-63-7		C	C	C	A	C	A	A	A
AMYL ALCOHOL		100	1105			B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
AMYL CHLORIDE		100	1107			C	C	C	B	C	A	A	A
ANILINE		100	1547	62-53-3		A	A	A	A	A	A	A	A
ANIMAL OILS		100	1373			A	A	A	A	A	A	A	A
ANISOLE		100	2222	100-66-3		C	C	C	B	C	D	A	D
ANTIFREEZE		100				A	A	A	A	A	A	A	A
ANTIMONY CHLORIDE		ALL	3141			D	B	B	B	B	D	A	A
APPLE JUICE		100				D	A	D	A	D	D	A	D
AQUA REGIA			1798			D	C	D	D	D	D	D	D
AROMATIC SPIRITS			1169			B	B	B	B	B			
ARSENIC ACID		80	1553	7778-39-4		D	B	C	B	C	D	A	A
ARSENIC CHLORIDE			1560	7784-34-1		D	B	D	D	D			
ASPHALT		100				D	D	D	A	D	A	A	A
AVIATION FUEL		100	1863			C	C	C	B	C	A	A	A
B													
BARIUM CARBONATE			1564 (001)			A	A	A	A	A			
BARIUM CHLORIDE SOL.			1564 (002)	10361-37-2		D	A	D	D	D			
BARIUM HYDROXIDE			1564 (004)	17194-00-2		D	A	A	A	A			
BARIUM SULPHATE			FREE			D	A	A	A	A			
BARIUM SULPHIDE			1564 (006)	21109-95-5		D	A	A	A	A			
BARIUM SALTS		SATURATED				D	A	B	A	B	A	A	D
BEER			FREE			D	A	A	A	A	A	A	A
BENZALDEHYDE			1990			D	C	C	A	C	D	A	D
BENZENE (BENZOL)			1114	71-43-2		D	C	C	A	C	A	A	A
BENZENE SULPHONIC ACID		100				D	C	D	B	D	D	A	D
BENZOIC ACID			3004			D	A	A	A	A	A	A	D
BENZOYL CHLORIDE		100	1736	98-88-4		C	C	C	C	C	A	A	A
BENZYL ACETATE						D	B	B	A	B			
BENZYL ALCOHOL		100	FREE			A	A	A	A	A	A	A	A
BENZYL BUTYL PHTHALATE						B	B	B	B	B			
BEZYL CHLORIDE			1738	100-44-7		D	D	D	D	D			
BISMUTH CARBONATE		SATURATED				D	A	D	A	D	A	A	D
BLEACH LIQUOR		12,5	1791	7981-52-9		D	B	C	B	C			
BORAX		SATURATED	FREE			A	A	A	A	A	A	A	D
BORIC ACID						D	A	A	A	A			
BRINE		SATURATED				D	A	D	D	D	D	A	D
BROMINE		100				D	D	D	D	D	D	D	D
BUNKER OIL						B	B	B	A	B			
BUTADIENE		100	1010	106-99-0		B	B	B	B	B	A	A	A
BUTANOL			1120			B	B	B	B	B			
BUTTER		100				D	D	D	D	D	D	A	D
BUTYL ACETATE			1123			C	C	C	A	C			
BUTYL ACRYLATE			2348	141-32-2		B	B	B	B	B			
BUTYL ALCOHOL			1120			A	A	A	A	A			
BUTYL AMINE			1125	109-73-9		D	B	B	B	B			
BUTYL BENZENE			2709	68411-44-9		B	B	B	B	B			
BUTYL BENZYL PHTHALATE			3082			B	B	B	B	B			

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
BUTYL BROMIDE		100	1126	109-65-9		D	D	D	B	D	A	A	A
BUTYL BUTYRATE			3272 (001)	109-21-7		B	B	B	B	B			
BUTYL CARBITOL						A	A	A	A	A			
BUTYL CARBITOL ACETATE						C	C	C	A	C	A	A	A
BUTYL CELLULOSE						A	A	A	A	A	A	A	A
BUTYL CELLULOSE ACETATE						C	C	C	B	C	A	A	D
BUTYL CHLORIDE			1127			D	D	D	B	D			
BUTYL/DECYL/CETYL-EICOSYL METHACRYLATE MIXTURE						D	D	D	B	D	D	A	D
BUTYL DIETHOXOL						D	B	B	B	B			
BUTYLENE GLYCOL		100	1012	106-98-9		A	A	A	A	A	A	A	A
BUTYL ETHER			1149			B	B	B	A	B	A	A	A
BUTYL ETHYL ETHER			1179	628-81-9		B	B	B	A	B	A	A	A
BUTYL METHACRYLATE			2227	97-88-1		C	C	C	A	C	A	A	A
BUTYL METHOXYETHYL ETHER						C	C	C	A	C	A	A	A
BUTYL PHTHALATE						A	A	A	A	A	A	A	A
BUTYL STEARATE						B	B	B	A	B	A	A	A
BUTYRALDEHYDE			1129	123-72-8		C	C	C	A	C	D	A	D
BUTYRIC ACID		20	2820	107-92-6		B	B	B	A	B	A	A	A
BUTYRIC ANHYDRIDE			2739	106-31-0		B	B	B	B	B			
BUTYROLACETONE						C	C	C	A	C	A	A	A
CALCIUMALKYL PHENATE						B	B	B	B	B			
CALCIUM ALKYL SALICYLATE SOLUTION						D	A	A	A	A	A	A	A
CALCIUM ALUMINATE						D	A	A	A	A			
CALCIUM BISULPHATE			2693			D	A	A	A	A			
CALCIUM CHLORIDE		SATURATED	1453			D	A	C	C	C	A	A	A
CALCIUM HYDROXIDE			FREE			D	A	A	A	A			
CALCIUM HYPOCHLORITE		20	2880	7778-54-3		D	B	C	C	C	D	A	D
CALCIUM NITRATE			1454	10124-37-5		D	A	A	A	A			
CALCIUM SALTS		SATURATED				D	A	A	A	A	A	A	
CALCIUM SILICATE			FREE			A	A	A	A	A			
CALCIUM SULPHATE						D	A	A	A	A			
CALCIUM SULPHIDE			3262	20548-54-3		D	A	A	A	A			
CALCIUM SULPHITE			3262	20548-54-3		D	A	A	A	A			
CALCIUM SULPHYDRATE						D	A	A	A	A			
CAMPHOR OIL			1130	92201-50-8		C	C	C	A	C	A	A	A
CAPRYLIC ACID			3265 (007)			A	A	A	A	A	A	A	A
CARBINOLS			1230	67-56-1		B	B	B	A	B	A	A	A
CARBITOLS						B	B	B	A	B	A	A	A
CARBITOLS ACETATE						C	C	C	A	C	A	A	A
CARBOLIC ACID			2821	108-95-2		D	A	A	A	A			
CARBOLIC OIL						C	C	C	A	C	A	A	A
CARBON BISULPHIDE			1131	75-15-0		D	B	B	B	B			
CARBON DISULPHIDE		100	1131	75-15-0		D	D	D	A	D	A	A	A
CARBON MONOXIDE			1016	630-08-0		D	A	A	A	A			
CARBON TETRACHLORIDE			1846	56-23-5		C	C	C	A	C	A	A	A
CARBONIC ACID						D	A	A	A	A	D	A	A
CASHEW NUTSHELL OIL			FREE			B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
CASTOR OIL		100	FREE			D	B	B	B	B	A	A	D
CAUSTIC POTASH		50	1814	1310-58-3		D	A	B	A	B	A	A	D
CAUSTIC SODA		50	1823	1310-73-2		C	A	B	A	B	A	A	D
CELLOSOLVE						B	B	B	B	B			
CETYL ALCOHOL			FREE			D	B	B	B	B			
CHLORINATED SOLVENTS			3082			D	B	B	B	B			
CHLORO ACETIC ACID		100	1750	79-11-8		D	B	D	D	D	D	D	D
CHLORINE WATER		SATURATED				D	C	D	D	D	D	D	D
CHLORINE			1017	7782-50-5		D	D	D	D	D			
CHLOROBENZENE			1134	108-90-7		C	C	C	A	C	A	A	A
CHLOROBUTANE			1127			C	C	C	A	C	A	A	A
CHLOROFORM			1888	67-66-3		C	C	C	A	C	A	A	A
CHLOROHYDRINS						C	C	C	A	C	D	A	D
CHLOROPRENE			1991	126-99-8		C	C	C	A	C	D	A	A
CHLOROPROPIONIC ACID			2511	598-78-7		D	C	D	D	D	D	D	D
CHLOROSULPHONIC ACID		100	1834	7791-25-5		D	D	D	D	D	D	D	D
CHLOROTHENE						B	B	B	B	B			
CHLOROTOLUENE		100	2238	95-49-8		C	C	C	A	C	A	A	D
CHROME ALUM		SATURATED				D	A	A	A	A	A	A	A
CHROMIC ACID AQUEOUS		50	1755	1333-82-0		D	C	C	B	C	D	A	A
CITRIC ACID		100	FREE			D	A	A	A	A	D	A	A
CLOVE OIL		100				C	C	B	A	B	A	A	A
COAL TAR NAPHTHA			1268			B	B	B	A	B	A	A	A
COPPER SALTS		SATURATED				D	B	B	A	B	A	A	D
COPPER CHLORIDE		SATURATED				D	A	D	D	D	D	D	D
CREOSOTE		100				B	B	B	A	B	A	A	A
CRESOLS		90				B	B	B	A	B	A	A	A
CRESYLIC ACIDS		90				B	B	B	A	B	A	A	A
CROTONALDEHYDE		100				D	D	D	A	D	A	A	D
CUMENE		100				B	B	B	A	B	A	A	A
CYCLOHEXANE		100				B	B	B	A	B	A	A	A
CYCLOHEXANOL		100				B	B	B	A	B	A	A	A
CYCLOHEXANONE		100				C	C	C	A	C	A	A	A
CYCLOHEXYLAMINE		100				B	B	B	A	B	A	A	A
CYCLOPENTANE		100				B	B	B	A	B	A	A	A
P.CYMENE		100				B	B	B	A	B	A	A	A
DECALIN		100	1147	91-17-8		D	D	D	A	D	D	A	D
DECANOL			3082			B	B	B	B	B			
DECYL ALCOHOL		100				B	B	B	A	B	A	A	A
DECYL ACRYLATE		100	3082			B	B	B	A	B	A	A	A
DECYL BUTYL PHTHALATE						B	B	B	B	B			
DETERGENTS		5				A	A	A	A	A	A	A	A
DEXYTRIN		100				A	A	A	A	A	A	A	A
DIACETONE ALCOHOL		100	1148	123-42-2		B	B	B	A	B	A	A	A
DIAMINOETHYLAMINE		100				D	B	B	A	B	A	A	A
DIAMYLAMINE		100	2841	2050-92-2		D	B	B	A	B	A	A	A
DIBROMOETHANE		100	1605	106-93-4		D	B	B	A	B	A	A	A
DIBUTYLAMINE		100	2248	111-92-2		C	B	B	A	B	A	A	

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
DIBUTYL ETHER		100	1149			C	C	C	A	C	A	A	A
DIBUTYL PHTHALATE		100				B	B	B	A	B	A	A	A
DIBUTYL SEBACATE		100				B	B	B	A	B	A	A	A
DICHLOROACETIC ACID		100	1764	79-43-6		D	C	D	D	D	D	D	D
DICHLOROBENZENE		100	1591	95-50-1		C	C	C	A	C	A	A	A
DICHLOROBUTANE		100				C	C	C	A	C	A	A	A
DICHLOROETHANE			2362	75-34-3		C	C	C	A	C			
DICHLOROETHYLENE		100	1150	540-59-0		C	C	C	B	C	A	A	A
DICHLOROETHYL ETHER		100	1916	111-44-4		C	C	C	A	C	A	A	A
DICHLOROISOPROPYL ETHER			2490			C	C	C	B	C			
DICHLOROMETHANE		100	1593			C	C	C	A	C	A	A	A
DICHLOROPHENOL			2021	95-57-8		C	C	C	B	C			
DICHLOROPROPANE		100	1993 (011)	79-99-9		C	C	C	A	C	A	A	A
DICHLOROPROPENE			2047	563-58-6		C	C	C	B	C			
DICHLOROPROPYLENE		100				C	C	C	A	C	A	A	A
DICHLOROPROPIONIC ACID						D	C	D	C	D	D	A	D
DICYCLOPENTADIENE			2048	77-73-6		D	D	D	D	D	D	D	D
DIESEL OIL		100	1202	64741-44-2		B	B	B	A	B	A	A	A
DIETHANOLAMINE		100	FREE			D	A	A	A	A	A	A	A
DIETHYLAMINE		100	1154	109-89-7		D	B	B	A	B	A	A	A
DIETHYLAMINOETHANOL		100	2686	100-37-8		C	B	B	A	B	A	A	A
DIETHYLBENZENE		100	2049	25340-17-4		B	B	B	A	B	A	A	A
DIETHYLENE DIOXIDE			1165	123-91-1		D	B	B	A	B			
DIETHYLENE GLYCOL		100				A	A	A	A	A	A	A	A
DIETHYLENE GLYCOL DIETHYL ETHER						B	B	B	A	B	A	A	A
DIETHYLENE GLYCOL MONOBUTYL ETH.						C	C	C	A	C	A	A	A
DIETHYLENE GLYCOL MONOETHYL ETH.						C	C	C	A	C	A	A	A
DIETHYLENE GLYCOL MONOETHYL ETH. ACETATE						C	C	C	A	C	A	A	A
DIETHYLENE GLYCOL MONOMETHYL ETH.						C	C	C	A	C	A	A	A
DIETHYLENE TRIAMINE		100				D	B	B	A	B	A	A	A
DIETHYL ETHANOLAMINE			2686	100-37-8		D	B	B	A	B	A	A	A
DIETHYL ETHER		100	1155	60-29-7		B	B	B	A	B	A	A	A
DIETHYL KETONE		100	1156	96-22-0		B	B	B	A	B	A	A	A
DIETHYL OXALATE		100	2525	95-92-1		B	B	B	A	B	A	A	A
DIETHYL PHTHALATE		100				A	A	A	A	A	A	A	A
DIETHYL SEBACATE		100				A	A	A	A	A	A	A	A
DIETHYL SULPHATE		100	1594	64-67-5		D	B	B	A	B	A	A	A
DIISOBUTYLAMINE			2361			B	B	B	B	B			
DIISOBUTYLENE			2050	25167-70-8		C	C	C	A	C	A	A	A
DIISOBUTYL KETONE		100	1157	108-83-8		B	B	B	A	B	A	A	A
DIISOBUTYL PHTHALATE		100				B	B	C	A	C	A	A	A
DIISOCTYL ADIPATE			FREE			B	B	B	A	B			
DIISOPROPANOL AMINE		100	FREE			D	B	B	A	B	A	A	A
DIISOPROPYL AMINE		100	1158	108-18-9		D	B	B	A	B	A	A	A
DIISOPROPYL ETHER		100	1159	108-20-3		B	B	B	A	B	A	A	A
DIISOPROPYL KETONE		100	1224 (002)	565-80-0		B	B	B	A	B	A	A	A
DIMETHYLAMINE		100	1160	124-40-3		B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
DIMETHYLCYCLOHEXYLAMINE			2264	42195-92-6		D	B	B	B	B			
DIMETHYL ETHANOLAMINE			2051	108-01-0		D	B	B	A	B	A	A	A
DIMETHYL ETHER		100				C	C	A	A	A	A	A	A
DIMETHYL FORMAMIDE		100	2265	68-12-2		A	A	A	A	A	A	A	A
DIMETYL KETONE			1090	67-64-1		A	A	A	A	A			
DIMETHYL PHTHALATE		100	FREE			B	B	B	A	B	A	A	A
DIMETHYL SULPHATE			1595	77-78-1		D	B	B	A	B	A	A	A
DIMETYL SULPHIDE		100	1164	287-92-3		B	B	B	A	B	A	A	A
DINITROBENZENE		100	1597			C	C	C	A	C	A	A	A
DIOCTYLAMINE						B	B	B	A	B			
DIOCTYL PHTHALATE		100	FREE			B	B	B	A	B	A	A	A
DIOCTYL SEBACATE		100				B	B	B	A	B	A	A	A
DIOXANE		100	1165	123-91-1		B	B	B	A	B	A	A	A
DIPENTENE		100	2052	138-86-3		B	B	B	A	B	A	A	A
DIPHENYL ETHER		100				B	B	B	A	B	A	A	A
DIPHENYL PHTHALATE		100				B	B	B	A	B	A	A	A
DIPROPYLAMINE		100	2383	142-84-7		B	B	B	A	B	A	A	A
DIPROPYLENE GLYCOL		100	FREE			A	A	A	A	A	A	A	A
DIPROPYLENE GLYCOL MONOMETHYL ETHER			FREE			C	C	C	A	C	A	A	A
DISULPHERIC ACID			1831			D	D	D	B	D			
DODECYL ALCOHOL						B	B	B	A	B			
DODECYL BENZENE		100				B	B	B	B	B	A	A	A
DODECYL PHENOL		100	3145			B	B	B	B	B	A	A	A
DODECYL METHACRYLATE						D	D	D		D			
DODECYL TOLUENE						B	B	B	B	B			
E													
EPICHLOROHYDRIN		100	2023	106-89-8		B	B	B	A	B	A	A	A
ETHANOL		100	1170	64-17-5		A	A	A	A	A	A	A	A
ETHANOLAMINE		100	2491	141-43-5		B	A	A	A	A	A	A	A
ETHOXY ETHANOL			1171	110-80-5		C	C	C	A	C	A	A	A
ETHOXY ETHYL ACETATE		100	1172	111-15-9		C	C	C	B	C	A	A	A
ETHOXY PROPANOL			2615	628-32-0		C	C	C	A	C	A	A	A
ETHYL ACETATE		100	1173	141-78-6		C	C	C	A	C	A	A	A
ETHYL ACRYLATE		100	1917	140-88-5		B	B	B	A	B	A	A	A
ETHYL ALCOHOL			1170	64-17-5		A	A	A	A	A			
ETHYL ALUMINIUM DICHLORIDE			3052			D	D	D	D	D	D	D	D
ETHYLAMINE		100	1036	75-04-7		C	B	B	A	B	A	A	A
ETHYLBENZENE		100	1175	100-41-4		B	B	B	A	B	A	A	A
ETHYL BUTANOL		100	2275	97-95-0		B	B	B	A	B	A	A	A
ETHYL BUTYLAMINE						C	B	B	B	B			
ETHYL CHLORIDE		100	1037	75-00-3		C	C	C	A	C	A	A	A
ETHYL CYCLOHEXANE						C	C	C	A	C	A	A	A
ETHYL CYCLOHEXYLAMINE			2734 (001)	5459-93-8		C	C	C	B	C			
ETHYL ETHER			1155	60-29-7		D	C	C	A	C			
ETHYL FORMATE		100	1190	109-94-4		D	B	B	A	B	A	A	A
ETHYL HEXANOIC ACID						D	B	B	B	B			
ETHYL HEXYL ACRYLATE		100				D	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
GLYCERINE		ALL	FREE			A	A	A	A	A	A	A	A
GLYCOLS AQUEOUS		ALL	FREE			A	A	A	A	A	A	A	A
GLYCOLIC ACID AQUEOUS						D	A	A	A	A			
GREASE						B	B	B	B	B			
GREEN SULPHATE LIQUOR						D	B	B	B	B			
H													
HEPTANE			1206	31394-54-4		B	B	B	A	B	A	A	A
HEPTANOIC ACID						D	B	B	A	B	D	A	D
HEPTANOL		100				A	A	A	A	A	A	A	A
HEPTANONE		100	1206	31394-54-4		B	B	B	A	B	A	A	A
HEPTENE		100	2278	592-76-7		B	B	B	A	B	A	A	A
HEXAMETHYLENE DIAMINE		100	1783	124-09-4		D	B	B	A	B	A	A	A
HEXAMETHYLENE IMINE			2493	111-49-9		D	C	C	B	C			
HEXAMETHYLENE TETRAMINE		100	1328	100-97-0		D	B	B	A	B	A	A	A
HEXANE		100	1208			B	B	B	A	B	A	A	A
HEXANOL		100	2282	111-27-3		A	A	A	A	A	A	A	A
HEXENE			2370	592-41-6		B	B	B	B	B			
HEXYLAMINE		100				D	B	B	A	B	A	A	A
HEXYLENE		100	2370	592-41-6		B	B	B	A	B	A	A	A
HEXYLENE GLYCOL		100				A	A	A	A	A	A	A	A
HYDRAZINE HYDRATE			2030	7803-57-8		D	B	B	A	B	D	A	D
HYDROBROMIC ACID		50	1788	10035-10-6		D	A	D	D	D	D	D	D
HYDROCHLORIC ACID		30	1789	7647-01-0		D	C	D	D	D	D	D	D
HYDROCHLORIC ACID AQUEOUS		37				D	C	D	D	D	D	D	D
HYDROCYONIC ACID		SATURATED				D	A	D	A	D	D	A	D
HYDROFLUORIC ACID		60	1790	7664-39-3		D	B	D	D	D	D	D	D
HYDROFLUORIC ACID		40	1790	7664-39-3		D	A	D	D	D	D	D	D
HYDROFLUOSLICIC ACID		20	1778			D	A	A	A	A	D	A	A
HYDROGEN BROMIDE						D	C	D	D	D	D	D	D
HYDROGEN CHLORIDE						D	C	D	D	D	D	D	D
HYDROGEN PEROXIDE SOLUTION		90	2984	7722-84-1		D	B	B	B	B	D	A	A
HYDROGEN SULPHIDE AQUEOUS		SATURATED	1053	04-06-7783		D	A	D	D	D	D	D	D
HYDROQUINONE		100				A	A	A	A	A	A	A	A
2-HYDROXYETHYL ACRYLATE		100	2810 (031)			C	C	C	A	C	A	A	A
HYDROXYETHYL ETHYLENE DIAMINE		100	2810 (032)			C	C	C	A	C	A	A	A
IODINE SOL.		SATURATED	1792	7790-99-0		D	B	D	D	D	A	A	A
FERRIC NITRATE			1466	10421-48-4		D	A	D	A	D			
IRON SALTS		SATURATED				D	A	A	A	A	A	A	D
IRON HALIDES		SATURATED				D	A	D	D	D	D	D	D
ISOAMYL ACETATE			1104			C	C	C	A	C	A	A	A
ISOAMYL ALCOHOL		100	1105			B	B	B	A	B	A	A	A
ISOAMYL BROMIDE		100	2341	107-82-4		D	B	D	D	D	D	A	D
ISOAMYL BUTYRATE		100	2620	540-18-1		D	B	B	A	B	A	A	A
ISOAMYL CHLORIDE		100				D	C	D	A	D	D	A	D
ISOAMYL ETHER		100				B	B	B	A	B	A	A	A
ISOBUTYL ACETATE		100	1213	110-19-0		C	C	C	A	C	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
ISOBUTYL ACRYLATE		100	2527	106-63-8		B	B	B	A	B	A	A	A
ISOBUTYL ALCOHOL		100	1212	78-83-1		A	A	A	A	A	A	A	A
ISOBUTYLAMINE		100	1214	78-81-9		D	B	B	A	B	A	A	A
ISOBUTYL BROMIDE		100	2342	78-77-3		D	B	D	D	D	D	A	D
ISOBUTYL CHLORIDE		100				D	B	D	D	D	D	A	D
ISOBUTYL ETHER		100				C	C	C	A	C	A	A	A
ISOBUTYL FORMATE			2393	542-55-2		C	C	C	C	C			
ISOBUTYL METHYL KETONE		100				B	B	B	A	B	A	A	A
ISOBUTYRALDEHYDE		100	2045	78-84-2		D	D	D	A	D	A	A	A
ISODECYL ALCOHOL		100				A	A	A	A	A	A	A	A
ISOOCTANE		100	1262			C	C	C	A	C	A	A	A
ISOPENTANE		100	1265	109-66-0		C	C	C	A	C	A	A	A
ISOPENTENE		100	2371			C	C	C	A	C	A	A	A
ISOPHORONE DIAMINE		100	2289	2855-13-2		D	C	D	B	D	D	A	D
ISOPHORONE DIISOCYANATE			2290			C	C	C	B	C			
ISOPRENE		100	1218	78-79-5		B	B	B	A	B	D	A	D
ISOPROPANOL			1219	67-63-0		D	B	B	A	B			
ISOPROPANOLAMINE		100				D	B	B	A	B	A	A	A
ISOPROPYL ACETATE		100	1220	108-21-4		C	C	C	A	C	A	A	A
ISOPROPYL ALCOHOL		100	1219	67-63-0		A	A	A	A	A	A	A	A
ISOPROPYLAMINE		100	1221	75-31-0		D	B	B	A	B	A	A	A
ISOPROPYL BENZENE			1918	98-82-8		B	B	B	B	B			
ISOPROPYL CHLORIDE		100	2356	75-29-6		D	B	D	B	D	D	A	A
ISOPROPYL ETHER		100	1159	108-20-3		D	B	D	B	D	A	A	A
ISOPROPYL TOLUENE			2046			B	B	B	B	B			
ISOVALERALDEHYDE		100	2058	110-62-3		D	D	D	A	D	A	A	A
J													
JAMS		100				B	A	A	A	A	A	A	A
JET FUEL		100				C	C	C	A	C	A	A	A
K													
KEROSENE		100	1223	8008-20-6		B	B	B	A	B	A	A	A
KETONES			1224			B	B	B	A	B			
L													
LACTIC ACID		20				D	A	B	A	B	A	A	A
LACQUER		100				C	C	A	A	A	A	A	A
LACQUER SOLVENTS		100				C	C	A	A	A	A	A	A
LANOLIN						A	A	A	A	A	A	A	A
LARD						A	A	A	A	A	A	A	A
LATEX			FREE			A	A	A	A	A	A	A	A
LAURYL ALCOHOL						B	B	B	A	B			
LEAD ACETATE			1616	301-04-2		D	A	A	A	A			
LEAD SALTS		SATURATED	1469	10099-74-8		D	A	B	B	B	D	A	D
LEMON OIL		100				C	C	A	A	A	A	A	D
LIGROIN		100	1268			C	C	C	A	C	A	A	A
LIMONENE		100	2052	138-86-3		B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	PP	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS	MILD STEEL	STAINLESS STEEL	BRASS
LINSEED OIL		100	1386			A	A	A	A	A	A	A	A
LUBRICATION OIL		100				B	B	B	A	B	A	A	A
M													
MACHINE OIL		100				A	A	A	A	A	A	A	A
MAGNESIUM SALTS		SATURATED				D	A	B	B	B	D	A	D
MAGNESIUM NITRATE			1474	10377-66-9		D	A	B	B	B	D	A	D
MALEIC ACID IN SOL.		100				D	A	B	B	B	D	A	A
MALEIC ANHYDRIDE IN SOL.			2215	108-31-6		D	B	B	B	B			
MALIC ACID IN SOL.		100				D	B	B	B	B	D	A	D
MANGANESE SALTS		SATURATED	2724	10377-66-9		D	A	B	B	B	D	A	D
MEAT JUICES			FREE			D	A	A	A	A			
MERCURIC CHLORIDE		SATURATED	1624	7487-94-7		D	A	D	D	D	D	D	D
MESITYL OXIDE		100	1229	141-79-7		B	B	B	A	B	A	A	A
METHACRYLIC ACID		SATURATED	2531	79-41-4		D	B	B	A	B	A	A	A
METHANOL		100	1230	67-56-1		A	A	A	A	A	A	A	A
METHAXYLENE						D	B	B	B	B			
METHYL ACETATE		100	1231	79-20-9		C	C	C	A	C	A	A	A
METHYL ACETO ACETATE		100				D	C	C	B	C	D	A	A
METHYL ACETONE		100				B	B	B	A	B	A	A	A
METHYL ACRYLATE		100	1919	96-33-3		B	B	B	A	B	A	A	A
METHYL ALCOHOL			1230	67-56-1		A	A	A	A	A			
METHYLAMINE			1235	74-89-5		C	B	B	B	B	A	A	A
METHYLAMYL ACETATE		100	1233	628-95-5		C	C	C	A	C	A	A	A
METHYLAMYL ALCOHOL		100	2053	108-11-2		B	B	B	A	B	A	A	A
METHYLAMYL KETONE		100	1110	110-43-0		B	B	B	A	B	A	A	A
METHYL BUTYL ALCOHOL						A	A	A	A	A			
METHYL TERT-BUTYL ETHER						C	C	C	A	C	A	A	A
METHYL BUTYL KETONE		100				B	B	B	A	B	A	A	A
METHYL BUTYRALDEHYDE			3082			D	D	D	A	D	D	A	D
METHYL CARBITOL						A	A	A	A	A			
METHYL CELLOSOLVE			1188	109-86-4		B	B	B	B	B			
METHYL CELLULOSE ACETATE		100				C	C	C	B	C	A	A	A
METHYL CELLULOSE		100				B	B	B	A	B	A	A	A
METHYL CHLORIDE		100	1063	74-87-3		C	C	C	A	C	A	A	A
METHYL CYANIDE		100	1648	75-05-8		B	B	B	A	B	A	A	A
METHYL CYCLOHEXANE		100	2296	108-87-2		B	B	B	A	B	A	A	A
METHYLENE BROMIDE		100	2664	74-95-3		C	C	C	A	C	A	A	A
METHYLENE CHLORIDE		100	1593	75-09-2		C	C	C	B	C	A	A	A
METHYL ETHYL KETONE		100	1193	78-93-3		C	C	C	A	C	A	A	A
METHYL ETHYLPYDRINE			2300	104-90-5		C	C	C	B	C	A	A	D
METHYL FORMATE			1243	107-31-3		C	C	C	A	C			
METHYL HEPTYL KETONE						D	B	B	B	B			
METHYL ISOBUTYL KETONE			1245	108-10-1		C	C	C	A	C	A	A	A
METHYL METHACRYLATE		100	1247	80-62-6		C	C	C	A	C	A	A	A
METHYL NITROBENZENE						B	B	B	B	B			
METHYL PENTENE						B	B	B	A	B			

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
2-METHYL PENTENE						C	C	C	A	C	A	A	A
METHYL PYRIDRINE			2313			D	B	B	B	B			
METHYL STYRENE		100	2303	98-83-9		B	B	B	A	B	A	A	A
MINERAL OIL		100				B	B	B	A	B	A	A	A
MINERAL SPIRITS		100				B	B	B	A	B	A	A	A
MOLASSES						A	A	A	A	A	A	A	A
MONOCHLORO BENZENE			1134	108-90-7		B	B	B	B	B			
MONOETHANOLAMINE			2491	141-43-5		B	A	A	A	A	A	A	A
MONOETHYL ETHER		100				A	A	A	A	A	A	A	A
MONOETHYLAMINE			1036	75-04-7		C	B	B	A	B	A	A	A
MONOISOPROPANOLAMINE			3267			D	B	B	B	B			
MONONITROBENZENE						B	B	B	A	B	A	A	A
MORPHOLINE		100	2054	110-91-8		B	B	B	A	B	A	A	A
N													
NAPHTA		100	1268			B	B	B	A	B	A	A	A
NAPHTA SOLVENT			1268			C	C	C	A	C	A	A	A
NAPHTALENE IN SOL.		100	2304	91-20-3		A	A	A	A	A	A	A	A
NEOHEXANE		100	1208			B	B	B	B	B	A	A	A
NICKEL CHLORIDE		SATURATED				D	A	D	D	D	D	D	D
NICKEL SALTS		SATURATED	2725	13138-45-9		D	A	D	B	D	D	A	D
NITRIC ACID		10	1796	51602-38-1		D	A	A	A	A	D	A	D
NITRIC ACID		30				D	B	B	B	B	D	A	D
NITRIC ACID		60	1826	51602-38-1		D	C	C	C	C	D	A	D
NITRIC ACID		70	1826	51602-38-1		D	D	D	C	D	D	A	D
NITROBENZENE		100				B	B	B	A	B	A	A	D
0-NITROPHENOL		100	1663			D	A	A	A	A	A	A	A
NITROPROPANE		100	2608			C	C	C	A	C	A	A	A
NITROTOLUENE		100	1664			B	B	B	A	B	A	A	A
NONANE		100	1920	111-84-2		B	B	B	A	B	A	A	A
NONYL ALCOHOL		100				B	B	B	A	B	A	A	A
NONYL PHENOL		100	3145			C	C	C	A	C	A	A	A
NUTMEG OIL		100				D	D	D	A	D	D	A	D
O													
OCTANE		100	1262			B	B	B	A	B	A	A	A
OCTANOL		100	FREE			B	B	B	A	B	A	A	A
OCTYL ACETATE		100				C	C	C	A	C	A	A	A
OCTYL ACRYLATE						B	B	B	A	B	A	A	A
OCTYL CARBINOL						B	B	B	B	B			
OILS						B	B	B	A	B	A	A	A
OLEIC ACID						D	B	B	A	B	D	A	D
OLEUM			1831			D	D	D	B	D	D	A	D
OLIVE OIL		100				D	D	D	A	D	D	A	D
OXALIC ACID		45	FREE			D	B	B	A	B	D	A	D
P													
PALM OIL		100	1386			B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
PARAFINE WAX			FREE			A	A	A	A	A			
1.3-PENTADIENE			3295	504-60-9		C	C	C	A	C	A	A	A
PENTANE		100	1265	109-66-0		B	B	B	A	B	A	A	A
PENTANOL		100	1105			A	A	A	A	A	A	A	A
PENTANONE		100	1249	107-87-9		B	B	B	A	B	A	A	A
PENTENE		100	1108	109-67-1		B	B	B	A	B	A	A	A
PERCHLORIC ACID		50	1873	7601-90-3		D	B	D	D	D	D	D	D
PERCHLOROETHYLENE			1897	127-18-4		C	C	C	A	C			
PETROLATUM		100	FREE			A	A	A	A	A	A	A	A
PETROLEUM		100	1268			A	A	A	A	A	A	A	A
PETROLEUM ETHER			1268			C	C	C	A	C			
PETROLEUM NAPHTA		100	1268			C	C	C	A	C	A	A	A
PHENOL		100	2821	108-95-2		C	A	B	A	B	A	A	D
PHENOXYETHANOL						C	C	C	B	C	A	A	A
PHENYLHYDRAZINE		100	2572	100-63-0		D	C	C	B	C	D	A	D
PHOSPHORUS						D	D	D	D	D	D	D	D
PHOSPHORUS BROMIDE			1808	7789-60-8		D	D	D	D	D	D	D	D
PHOSPHORIC ACID		96	1805	7664-38-2		D	A	A	A	A	D	A	D
PHOSPHORIC ACID		25	1805	7664-38-2		D	A	A	A	A	D	A	D
PHOSPHORUS OXYCHLORIDE			1810	10025-87-3		D	C	D	D	D	D	D	D
PHOSPHORUS PENTOXIDE			1807	1314-56-3		D	A	B	B	B	D	A	D
PHOSPHORUS TRICHLORIDE		100	1809	02-12-7719		D	B	D	D	D	D	D	D
PHTHALIC ACID		50				D	B	B	B	B	D	A	D
PHTHALIC ANHYDRIDE			2214	85-44-9		D	D	D	D	D			
PICRIC ACID AQUEOUS		1	1344	88-89-1		D	B	B	B	B	D	A	D
PINENE			2368	80-56-8		B	B	B	A	B	A	A	A
PINE OIL		100	1272			B	B	B	A	B	A	A	A
PLASTICISERS		100				B	B	B	A	B	A	A	A
POLYETHYLENE GLYCOL		100	FREE			B	B	B	A	B	A	A	A
POLYETHYLENE POLYAMINES						D	C	C	A	C	A	A	A
POLYPROPYLENE GLYCOL		100				B	B	B	A	B	A	A	A
POTASSIUM SALTS		SATURATED	0158			D	A	B	A	B	D	A	D
PROPANOIC ACID						D	B	B	A	B	A	A	A
PROPIOLACTONE			2810 (042)			C	C	C	A	C	A	A	A
PROPIONALDEHYDE		100	1275	123-38-6		D	C	C	A	C	A	A	A
PROPIONIC ACID		100	1848	79-09-4		D	B	B	A	B	D	A	A
PROPIONIC ANHYDRIDE			2496	123-62-6		D	C	C	B	C	D	A	A
PROPIONITRILE			2404			C	C	C	C	C			
PROPYL ACETATE		100	1276	109-60-4		C	C	C	A	C	A	A	A
PROPYL ALCOHOL		100	1274	71-23-8		A	A	A	A	A	A	A	A
PROPYLAMINE			1277	107-10-8		D	B	B	A	B	A	A	A
PROPYLENE DICHLORIDE		100				C	C	A	A	A	A	A	A
PROPYLENE GLYCOL			FREE			A	A	A	A	A			
PROPYLENE GLYCOL MONOETHYL ETHER						B	B	B	A	B	A	A	A
PROPYLENE GLYCOL MONOMETHYL ETHER			1993 (020)			B	B	B	A	B	A	A	A
PROPYLENE (TETRAMER)			2850			C	C	C	B	C	D	A	D
PROPYLENE OXIDE		100	1280	75-56-9		D	B	B	B	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
PRUSSIC ACID			1613	74-90-8		D	A	A	A	A	D	A	D
PYRIDENE		100	1282	110-86-1		D	B	B	A	B	A	A	A
PYROSULPHURIC ACID			1831			D	D	D	B	D			
S													
SALT SOLUTIONS						D	A	B	A	B	A	A	A
SEA WATER			FREE			D	A	B	B	B	D	A	A
SEWAGE						D	B	B	B	B	A	A	A
SILICON OIL						A	A	A	A	A	A	A	A
SILVER HALIDES		SATURATED				D	A	D	D	D	D	D	D
SILVER SALTS		SATURATED	1493	7761-88-8		D	A	B	B	B	A	A	A
SOAP SOLUTIONS						B	A	A	A	A	A	A	A
SODIUM CHLORIDE		SATURATED	1496	7758-19-2		D	A	D	D	D	D	D	D
SODIUM DICHROMATE						D	B	D	D	D			
SODIUM HYDROSULPHIDE			2949	16721-80-5		D	A	B	B	B	A	A	A
SODIUM HYDROXIDE			1824	1310-73-2		D	A	B	B	B	A	A	A
SODIUM HYPOCHLORITE		20	1791	7681-52-9		D	C	D	D	D	D	D	D
SODIUM SALTS		SATURATED	0203			D	A	B	B	B	A	A	A
SODIUM THIOSULPHATE		20				D	A	B	B	B	D	A	D
STARCH AQUEOUS						B	A	A	A	A	A	A	A
STYRENE MONOMER		100	2055	100-42-5		B	B	B	A	B	A	A	A
SUGAR SYROP			1386			A	A	A	A	A	A	A	A
SULPHAMIC ACID			2967	5329-14-6		D	A	A	A	A	D	A	D
SULPHUR DIOXIDE			1079	05-09-7446		D	C	C	C	C			
SULPHUR LIQUID			1828	10025-67-9		D	D	D	D	D	D	D	D
SULPHURIC ACID		< 20	2796	10043-01-3		D	B	B	B	B	A	A	D
SULPHURIC ACID		20 - 85	2796 / 1830	10043-01-3		D	B	D	D	D	D	D	D
SULPHURIC ACID		> 85	1830	7664-93-9		D	C	C	B	C	A	A	D
SULPHUROUS ACID			1833	7782-99-2		D	B	B	B	B	A	A	D
SULPHURYL CHLORIDE			1834	7791-25-5		D	D	D	D	D	D	D	D
T													
TALL OIL		100				A	A	A	A	A	A	A	A
TALLOW NITRILE		100	3082			A	A	A	A	A	A	A	A
TANNIC ACID		10				D	A	A	A	A	D	A	A
TARTARIC ACID						D	A	B	A	B	D	A	A
TETRACHLOROETHANE			1702	104-81-4		C	C	C	A	C	A	A	A
TETRACHLOROETHYLENE			1897	127-18-4		C	C	C	A	C	A	A	A
TETRAETHYLENE GLYCOL		100				B	B	B	A	B	A	A	A
TETRAETHYLENE PENTAMINE			2320	112-57-2		D	B	B	B	B	A	A	A
TETRAHYDROFURAN			2056	109-99-9		D	D	D	A	D	D	A	D
TETRAHYDRONAPHTALENE			FREE			C	C	C	A	C	A	A	A
TETRALIN		100				D	C	D	A	D	D	A	D
TIN HALIDES						D	A	D	D	D	D	D	D
TIN SALTS		SATURATED				D	A	D	D	D	A	A	A
TITANIUM TETRACHLORIDE			1838	7550-45-0		D	C	D	D	D	D	D	D
TOLUENE		100				C	C	C	A	C	A	A	A
TOLUENE DIISOCYANATE		100	2078	584-84-9		B	B	B	A	B	A	A	A

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
TRANSFORMER OIL		100				B	B	B	A	B	A	A	A
TRANSMISSION OIL		100				B	B	B	A	B	A	A	A
TRIBUTYLAMINE		100	2542	102-82-9		B	B	B	A	B	A	A	A
TRIBUTYL PHOSPHATE		100	FREE			B	B	B	A	B	A	A	A
TRICHLOROACETIC ACID		10	2564	76-03-9		D	A	D	D	D	D	D	D
TRICHLORO BENZENE		100	2321			D	C	C	A	C	A	A	A
TRICHLOROETHANE		100	2831	71-55-6		C	C	C	A	C	A	A	A
TRICHLOROETHYLENE		100	1710	79-01-6		C	C	C	A	C	A	A	A
TRICHLOROPROPANE		100				C	C	C	A	C	A	A	A
TRICRESYL PHOSPHATE		100	3082			B	B	B	A	B	A	A	A
TRIDECANOL		100	FREE			B	B	B	A	B	A	A	A
TRIETHANOLAMINE		100	FREE			D	B	B	B	B	A	A	A
TRIETHYLAMINE		100	1296	121-44-8		D	B	B	B	B	A	A	A
TRIETHYLBENZENE		100	3082			B	B	B	A	B	A	A	A
TRIETHYLENE GLYCOL		100				A	A	A	A	A	A	A	A
TRIETHYLENE TETRAMINE		100	2259	112-24-3		D	B	B	A	B	A	A	A
TRIMETHYL ACETIC ACID						D	A	A	A	A			
TRIMETHYLBENZENE		100	2325	108-67-8		B	B	B	A	B	A	A	A
TRIMETHYL HEXAMETHYLENE DIAMINE			2327			C	C	C	B	C			
TRIOCTYL PHOSPHATE		100				B	B	B	A	B	A	A	A
TRIPROPYLENE			2057	13987-01-4		A	A	A	A	A			
TRIPROPYLENE GLYCOL		100				A	A	A	A	A	A	A	A
TRIPROPYLENE GLYCOL MONOMETHYL ETHER						C	C	C	A	C	A	A	A
TRITOLYL PHOSPHATE		100				B	B	B	A	B	A	A	A
TRIXYLENYL PHOSPHATE		100	3082			B	B	B	A	B	A	A	A
TURPENTINE		100	1299	8006-64-2		C	C	C	A	C	A	A	A
U													
UREA AQUEOUS		SATURATED				B	A	B	A	B	A	A	D
UREA AMMONIA SOL.						B	A	B	A	B	A	A	D
UREA AMMONIUM SALTS SOL.						B	A	B	A	B	A	A	D
V													
VALERALDEHYDE			2058	110-62-3		C	C	C	A	C	A	A	A
VASELINE		100				A	A	A	A	A	A	A	A
VEGETABLE OIL		100	1373			A	A	A	A	A	A	A	A
VINEGAR			FREE			D	A	A	A	A	D	A	A
VINYL ACETATE			1301	108-05-4		D	B	B	A	B	D	A	A
VINYL ETHYL ETHER			1302	109-92-2		C	C	C	A	C	A	A	A
VINYL ACETATE			1301	108-05-4		D	C	C	C	C	D	C	C
VINYLDENE CHLORIDE			1303	75-35-4		C	C	C	A	C	A	A	A
VINYL NEODECANONATE						C	C	C	A	C	A	A	A
VINYL TOLUENE			2618	25013-15-4		B	B	B	A	B	A	A	A
W													
WATER			FREE			A	A	A	A	A	A	A	A
WHITE SPIRIT		100	1300	119-64-2		B	B	B	B	B	A	A	A
WINE			FREE			D	B	B	A	B	D	A	D

CONVEYANT	TEMPERATURE	CONCENTRATION	UN NUMBER	CAS NUMBER	ADR CLAS.	MOB	MCB	MCG	MCR	MCW	COUPLING TYPE		
INTERNAL WIRE FIRST LINNING	°C	%				GG PP	PP STEEL PP	SS PP	SS PTFE/HOS.	SS PP	MILD STEEL	STAINLESS STEEL	BRASS
X													
XYLENE		100	1307	1330-20-7		B	B	B	A	B	A	A	A
XYLENOL		100	2261			B	B	B	A	B	A	A	A
Y													
YEAST AQUEOUS						D	A	A	A	A	D	A	A
Z													
ZINC HALIDES						D	A	D	D	D	D	D	D
ZINC SALTS AQUEOUS						D	A	B	B	B	A	A	A